

QUELI®7030ME Saturated Polyester Resin

Product Description:	QUELI®P7030ME is a kind of saturated carboxyl polyester resin, mixed with epoxy resin in 70/30 for polyester/epoxy powder coatings.	
Product Properties:	QUELI®P7030ME is provided with; Excellent flow; Good mechanical properties; Perfect anti-yellowing; Good storage stability;	
Specifications:	Appearance:	Chip solid
	Color (50% DMF):	Max.3
	Acid Value (mgKOH/g):	28-34
	ICI viscosity (175℃)Po:	110-140
	Softening Point (ball)℃:	95-115
	Tg (℃):	Appr.52
Package and Shelf life:	25kgs net in bag. One year in dry and well-ventilated condition below 30℃. (If exceed shelf life, please check again. It can be used if inspection result is ok.)	
Starting Formulation:	QUELI®7030ME:	High gloss 420g
	Epoxy (E-12)/DER663U:	180g
	TiO ₂ (R902):	350g
	Pv88	10g
	Benzoin:	5g
Extrusion Condition:	Extruder:	BUSS PLK46
	Casing setting temperature℃	110-120
	Kneading screw temperature℃	60
	R.P.m:	60
	Particle size(μm):	Max100
	Curing Condition:	180℃ × 15min.(MT)
Film Properties:	Thickness(μm):	60 ± 10
	Gloss(60°)%:	Min.90
	Adhesion(2mm):	0-1
	Bending(mm):	Max.4
	Erichsen(mm):	Min.7
	Impact(kgcm):	50
	Hardness(pencil)H:	1H
Application Condition:	Degreased and stainless cold-rolled steel(mm):	0.5
	Spraying tension KV:	50



Address: Unit A, 4th Floor, No. 1 Building, Wanxin Mansion, No. 41 West Lake Road, Hangzhou, China
The First Farming Site of Xiaoshan District, Hangzhou, China
E-mail: hsfccq@mail.hz.zj.cn
http://www.dfc-cn.com

Foreign trade dept.: Tel: 0086 571 88093306
Fax: 0086 571 88092284
Domestic marketing dept: Tel: 0086 571 88094830
0086 571 88093580
Fax: 0086 571 88099166